



70026 Modugno (Bari) Italy - Via Agrigento, 37/39 Z.I.  
Tel. (+39) 080 5358845 - Fax (+39) 080 5358822  
www.marmoplast.it - info@marmoplast.it

*Technical Sheet* **Superstucco Esterni**

**ITEM CODE  
090**

*Anti humid powder filler for external use*

**GENERAL INSTRUCTIONS**

<b>Description</b>	<i>Fine powder filler for external use, resistant to humidity. This innovative product is based on a particular mixture of hard minerals, cement, additives, plasticizers and a very fine polymeric dispersion that makes it elastic and self-adhesive. It adheres on all sort of mineral supports.</i>
<b>Use</b>	<i>To fill and level deteriorated external walls, cement buildings. To smooth old scratch coat walls, avoiding taking off. It is also used internally to smooth walls that have been damaged from humidity.</i>
<b>Packaging</b>	<i>Kg. 15 - Kg. 5 - Kg. 1</i>
<b>Colours</b>	<i>White - Light grey</i>
<b>DIRECTIONS FOR USE</b>	
<b>How to apply</b>	<i>Substrate must be clean and without peeling. If necessary, it is recommended to wet the area with water. In a clean tank, pour water and add Superstucco Esterni till you get the right consistency. Apply the product with a spatula or a stainless steel float to get a 5-6 mm thickness. If necessary, sandpaper the area to smooth it. Wait for, at least, 3 days before painting.</i>
<b>Pot life of mix</b>	<i>About 2-3 hours</i>
<b>Application temperature</b>	<i>Between 10°C and 35°C. Humidity lower than 75%.</i>
<b>Dilution</b>	<i>Water.</i>
<b>Recommended tools</b>	<i>Spatula, stainless steel float.</i>
<b>Tools cleaning</b>	<i>With water, soon after use</i>
<b>Film final look</b>	<i>Compact</i>
<b>Drying process at 20°</b>	<i>According to the thickness. Dust dry in about 4-8 hours, a deep one in 12-24 hours for a 5mm thickness.</i>
<b>Storage</b>	<i>Keep the tank tightly closed, away from heat sources, for a maximum of 12 months from production date showed on the tin.</i>
<b>Cautions</b>	<i>Use rubber gloves. Always wear goggles and a mask when spraying. Aerate the room.</i>

This technical sheet is just informative. Colorificio Marmoplast has no responsibility with regards to a wrong application of the products.



70026 Modugno (Bari) Italy - Via Agrigento, 37/39 Z.I.  
 Tel. (+39) 080 5358845 - Fax (+39) 080 5358822  
 www.marmoplast.it - info@marmoplast.it

## Technical Sheet **Superstucco Esterni**

**ITEM CODE**  
**090**

*Anti humid powder filler for external use*

### TECHNICAL DATA

Coverage rate	<i>It varies according to the thickness: 1 mq/Kg per about 1mm</i>
Hazard class	<i>None.</i>
Specific weight	-
pH	-
Viscosity	-
VOC	-
PVC	-
% SVR	-
Certification	<i>n.a.</i>
Washability	-
Brightness	-
Adherence	<i>n.a.</i>
Notes	<i>n.a.</i>

This technical sheet is just informative. Colorificio Marmoplast has no responsibility with regards to a wrong application of the products.